



Petroleum Jelly Cosmetic Grade (A)

NO	CHARACTERISTIC	RESULT	ACCEPTED LIMIT
1	Kinematic viscosity at 100 ċ	5.8 cSt	4.5-6.5 cSt
2	Congeaing Point	53.5 ċ	51-55 ċ
3	Penetration Consistency	128 (0.1 mm)	120-130 (0.1 mm)
4	Color (Lovibond)	0.7 Y	Max 1 Y
5	Acidity or Alkalinity	Passed	According to the test method
6	Polycyclic aromatic Hydrocarbons	Passed	Not more than the absorbance of the solution 6 mg/l Naphthalene in DMSO@278 nm
7	Drop Melting Point	56 ċ	55-58 ċ
8	Odor	Passed	Odorless when rubbed on the hand



No. 2305 of the Burlington Tower, Business Bay, DUBAI-UAE



www.suhaco.ae



+971(4) 566 4998

+971(56)281 7292 (whatsapp)



info@suhaco.ae