



### Petroleum Jelly Cosmetic Grade (B)

| NO | CHARACTERISTIC                | RESULT       | ACCEPTED LIMIT                   | METHOD                |
|----|-------------------------------|--------------|----------------------------------|-----------------------|
| 1  | Kinematic viscosity at 100 °C | 6.2 cSt      | 6-8 cSt                          | ASTM D-445            |
| 2  | Congeaing Point               | 57.5 °C      | 54-58 °C                         | ASTM D-938            |
| 3  | Penetration Consistency       | 147 (0.1 mm) | 140-160 (0.1 mm)                 | ASTM D-937            |
| 4  | Color (Lovibond)              | 0.7 Y        | Max 0.7 Y                        | IP-17 Method A 2 cell |
| 5  | Acidity or Alkalinity         | Passed       | According to the test method     | B.P. 2007             |
| 6  | Odor                          | Passed       | Odorless when rubbed on the hand | —                     |