



Specification of Natural Rubber

Parameter	Unit	SMR CV50	SMR CV60	SMR L	SMR 5	SMR GP	SMR 10	SMR 10CV	SMR 20	SMR 20CV
Dirt (max)	%wt	0.02	0.02	0.02	0.05	0.08	0.08	0.08	0.16	0.16
Ash (max)	%wt	0.50	0.50	0.50	0.60	0.75	0.75	0.75	1.00	1.00
Nitrogen (max)	%wt	0.60	0.60	0.60	0.60	0.60	0.60	0.60	0.60	0.60
Volatile Matter (max)	%wt	0.80	0.80	0.50	0.80	0.80	0.80	0.80	0.80	0.80
Po (min)		NA	NA	35	30	NA	30	NA	30	NA
PRI Index (min)		60	60	60	60	50	50	50	40	40
Lovibond Color: individual value (max)		NA	NA	6.0	NA	NA	NA	NA	NA	NA
Lovibond Color: range (max)		NA	NA	2.0	NA	NA	NA	NA	NA	NA
Mooney Viscosity (ML, 1+4, 100°C)		50 +/- 5	60 +/- 5	NA	NA	65 +7/-5	NA	60 +7/-5	NA	65 +7/-5



No. 2305 of the Burlington Tower, Business Bay, DUBAI-UAE



www.suhaco.ae



+971(4) 566 4998

+971(56) 281 7292 (whatsapp)



info@suhaco.ae

