



## Specifications of Oxidized Polyethylene Wax (OPE)

| Product                       | Viscosity                    | Drop point | Penetration | Acid value |
|-------------------------------|------------------------------|------------|-------------|------------|
|                               | @ 140°C [mm <sup>2</sup> /s] | [°C]       | [0.1 mm]    | [mg KOH/g] |
| <b>Oxidized PE-Wax - 253</b>  | 200                          | 109        | ≤ 2         | 16         |
| <b>Oxidized PE-Wax - 252</b>  | 200                          | 106        | ≤ 3         | 16         |
| <b>Oxidized PE-Wax - 272</b>  | 170                          | 108        | ≤ 3         | 22         |
| <b>Oxidized PE-Wax - 271</b>  | 170                          | 104        | ≤ 4         | 22         |
| <b>Oxidized PE-Wax - 262</b>  | 150                          | 107        | ≤ 4         | 27         |
| <b>Oxidized PE-Wax - 261</b>  | 150                          | 103        | ≤ 5         | 27         |
| <b>Oxidized PE-Wax - 2628</b> | 50                           | 105        | ≤ 6         | 27         |



No. 2305 of the Burlington Tower, Business Bay, DUBAI-UAE



[www.suhaco.ae](http://www.suhaco.ae)



+971(4) 566 4998

+971(56)281 7292 (whatsapp)



[info@suhaco.ae](mailto:info@suhaco.ae)